

ADHERE FLEX TT PRO

INDOOR AND OUTDOOR DEFORMABLE CEMENT ADHESIVE

1. DESCRIPTION

ADHERE FLEX TT PRO is an improved construction adhesive with extended open time, reduced vertical sliding and deformable (Classification **C2 TE S1** according to EN 12004-1), formulated from mixed binders, limestone and siliceous aggregates and additions.

O **ADHERE FLEX TT PRO** is available in grey.

2. FIELD OF USE

ADHERE FLEX TT PRO is especially suitable for bonding large ceramic tiles with low absorption ($E \leq 0.5\%$) to interior and exterior walls and floors.

The substrates allowed can be: plaster, screed, concrete, plasterboard, among others. It is ideal for special applications such as ceramic tiles, screeds with heating/cooling systems, cementitious membranes, ornamental stone and swimming pools.

On external façades, it is recommended for bonding ceramic tiles to thermal insulation systems, up to 6 metres high. For non-standard applications or special circumstances contact our Commercial-Technical Service.

3. PRODUCT FEATURES

Powder product	Amount
Colour	Grey
Grade	< 1.0 mm
Paste product	Amount
Mixing water	29.0 % \pm 2.0 %
Sliding	≤ 0.5 mm
Hardened Product	Amount
Initial tensile adherence	≥ 1.0 N/mm ²
Tensile adherence after immersion in water	≥ 1.0 N/mm ²
Hardened Product	Amount
Tensile adherence after heat action	≥ 1.0 N/mm ²
Tensile adherence after freeze-thaw cycles	≥ 1.0 N/mm ²
Tensile adherence after extended open time (after 30 min.)	≥ 0.5 N/mm ²
Transverse deformation	≤ 2.5 mm
Reaction to fire	Class E

ADHERE FLEX TT PRO

INDOOR AND OUTDOOR DEFORMABLE CEMENT ADHESIVE

4. APPLICATION

a) Preparation of substrates

The substrates must be clean and free of dust, stripping oils, efflorescence and/or any other matter that could affect their adherence. They must also be even, flat and cohesive. The flattening can be checked using a 2 m metal ruler.

On highly absorbent substrates, moisten before application. **However, they must not be saturated with water at the time of application.**

For more demanding wall bonding, use **REDUR MAX FORCE** render and for floors we recommend using a floor screed filler layer of **PLAN FORCE**.

Always providelaying and/or fractionation joints so that they can absorb possible movements in the coating.

The ceramic tile must comply with the existing structural joints in the substrate, such as expansion joints. These must be made watertight by applying a suitable sealant.

Should the surface be an old ceramic bonding, it must be ensured that it is sturdy, smooth and all parts adhere well to the surface. If this is not the case, the loose parts should be removed and the coating smoothened. If necessary, clean the surface with suitable detergents to remove oils and residues accumulated on the surface.

b) Preparation of the mixture

ADHERE FLEX TT PRO should be mixed with 7.0 to 7.5 litres of clean drinking water per 25 kg bag using a low speed mixer until a homogeneous, lump-free paste is obtained.

Leave the mixture to stand for 5 minutes and mix again.

c) Application

Spread the mixture on the substrate using small sections, suitable for the temperature and humidity conditions. Smooth the surface with a comb or notched trowel suitable for the application. The piece to be glued must be pressed against the substrate with the aid of a rubber mallet until the adhesive strands are completely compressed.

Do not proceed with bonding when the open time has expired (see point 3.), which is confirmed by the appearance of a film of a different colour on the surface of the cementitious adhesive.

The joints between ceramic tiles must be at least 2 mm apart indoors and 5 mm apart outdoors.

When bonding polished natural stone, the back of the piece should be sanded to improve adherence.

For bonding ceramic tiles on ceramic tiles and for bonding elements with an area of more than 900 cm² outdoors, use the double bonding method.

When bonding coatings weighing more than 40 kg/m², mechanical fixing of the pieces is recommended.

d) Consumption

Theoretical consumption	Bonding method	
	Simple bonding	Double bonding
No. 6 notched trowel	4.0 kg/m ²	6.0 kg/m ²

ADHERE FLEX TT PRO

INDOOR AND OUTDOOR DEFORMABLE CEMENT ADHESIVE

e) Grouting and sealing

The joints between the tiles can be grouted after approximately 6 hours on the wall and after 24 hours on the floor with specific cementitious grouting mortars **ADHERE COR 05** or **ADHERE COR 312** available in various colours.

f) Restrictions

- **ADHERE FLEX TT PRO** should never be applied in isolated portions, but rather covering the entire substrate to be tiled with ceramic/natural stone. The same applies to the back of the parts to be glued when double bonding;
- **ADHERE FLEX TT PRO** should not be applied when the ambient and substrate temperature is below 5°C or above 30°C.
- Bonding should not be carried out outdoors in adverse weather conditions within 24 hours of application;
- In cases of strong exposure to wind, the façades should be protected to minimise its impact.

g) Complementary advice

- The mixing water must be free of impurities (clay, organic matter) and must be of drinking quality;
- Any mortar that has exceeded its open time must not be applied. Do not soften the mortar by adding water after preparation;
- Do not add any other products to the mortar, **ADHERE FLEX TT PRO** should be applied as it is presented in its original packaging;
- Consult the APFAC Ceramic-Adhesive System Application Manual.

5. PACKAGING AND VALIDITY

Packaging

Plastic pallets of 60 x 25kg paper bags.

Expiry Date

12 months, provided the original packaging conditions remain unchanged and in storage conditions protected from extreme temperatures and damp.

6. HYGIENE AND SAFETY

(DOES NOT PRECLUDE THE PRODUCT SAFETY DATA SHEET)

- Irritant to the eyes, respiratory system and skin
- May cause sensitivity in contact with the skin;
- Do not inhale the dust;
- Avoid contact with the skin and eyes;
- In case of contact with the eyes, wash immediately with plenty of water and consult a specialist;
- Wear suitable protective clothing and gloves
- Keep out of the reach of children.

ADHERE FLEX TT PRO

INDOOR AND OUTDOOR DEFORMABLE CEMENT ADHESIVE



25

ADHERE FLEX TT PRO

EN 12004:2007+A1:2012

NB: 0855 (CTCV)¹

Improved, deformable, elongated open-weather adhesive with reduced vertical slip for bonding tiles indoors and outdoors (C2TE S1)

Declaration of performance **DOP.01015** (grey)

Since the conditions of application of our products are out of our control, we cannot be held responsible for their incorrect use. It is the customer's responsibility to verify the suitability of the product for its intended purpose. In any case our liability is limited to the value of the goods provided by us. The information contained in this factsheet may be changed without notice. In case of doubt, and should you require further clarification, we recommend you contact our technical services.

Revision September 2025
FT.01015.02