

1. DESCRIPTION

ISOVIT FIBRA is a fibre-reinforced bonding and smoothing mortar made from mixed binders, selected aggregates and additions.

2. FIELD OF USE

ISOVIT FIBRA is specially designed for bonding and regularising sheets of EPS, XPS without film, mineral wool and cork agglomerate in external thermal insulation systems, on masonry substrates, cement blocks, thermal insulation boards and/or hydraulic-based substrates such as concrete and plaster.

ISOVIT FIBRA is suitable for renovation of the thermal insulation of painted or ceramic-tiled facades, as it allows exterior insulation systems to be bonded directly to this type of substrate in conjunction with the use of mechanical fixing – **ISOVIT BUCHA**.

For non-standard applications or special circumstances contact our Technical and Commercial Services.

3. PRODUCT FEATURES

Features	Amount	Standard
Colour	Grey	-
Grade	<1.0 mm	-
Paste product	Amount	Standard
Mixing water	25.0% ± 1.0%	-
Theoretical consumption	4 a 6 kg/m ² – Bonding 1.6 kg/m ² /mm – Smoothing	-
Hardened Product	Amount	Standard
Compressive strength	≥ 6 MPa	EN 1015-11
Adherence to brick / Fracture mode	≥ 0.8 MPa / A and B	EN 1015-12
Adherence to insulation board (EPS; XPS; ICB)	Leakage within the insulation	
Density	1350 ± 150 kg/m ³	EN 1015-6
Capillarity	Class W _c 2	EN 1015-18
Permeability to water vapour	≤ 20 μ	EN 1015-19

Reaction to fire	Class A1	EN 998-1
Thermal Conductivity	0.45 W/(m.°C) (P=50%)	NP EN 1745

4. APPLICATION

a) Preparation of substrates

Surfaces must be hardened, clean of dust, releasing agents, crumbling or unstable materials, efflorescences, as well as any type of material affecting the conditions of adherence.

The surfaces must be checked with a two-metre ruler, ensuring that there are no irregularities greater than 1 cm. Otherwise, the substrates should be regularised with **REDUR MAX FORCE** plaster.

Previously applied plasters must have a trowelled texture and cure for about 28 days, protected from the weather.

For application on painted surfaces, the paint must have sufficient adherence to support the new coating.

In the case of old ceramic tiles, the adherence and cohesion of all the pieces must be checked. Any loose parts should be removed and the surface regularised with **ISOVIT FIBRA**. If necessary, clean the surface with suitable detergents to remove oils and residues accumulated on the surface.

b) Preparation of the mixture

ISOVIT FIBRA should be mixed with 6.0 to 6.5 litres of clean water (preferably drinking water) for each bag of product, using an electric mixer, until a smooth paste is obtained.

c) Application

- Apply to masonry and uneven surfaces (gradient more than 1 cm every 2 metres)

Bond the panels by laying a continuous line of mortar around the perimeter, adding at least three bonding points in the centre of the panels. Provide for mechanical fixing with **ISOVIT BUCHA** (recommended minimum – 6 per/m²).

- Apply to even plaster or concrete surfaces

Simple continuous bonding should be carried out using a 10 mm jagged trowel, preferably placing the mortar on the back face of the panels. Provide for mechanical fixing with **ISOVIT BUCHA** (recommended minimum – 6 per/m²).

- Recommendations for bonding

The procedures for the development of bonding should ensure uniformity of surfaces, that the panels are level and without gaps and that there is no mortar between them.

- Regularisation

Skim **ISOVIT FIBRA** mortar on thermal insulation panels, conveniently arranged and adherent to the surfaces. Apply a first layer with an 8 mm notched trowel and immediately proceed to soak the fibreglass mesh suitable for the application - **ISOVIT REDE 160** or **ISOVIT REDE 343**.

Apply the second layer so as to completely hide the mesh and give the surfaces the flatness needed to receive the final finish. The total thickness of this layer must be at least 4 mm.

d) Restrictions

ISOVIT FIBRA should not be applied at ambient and surface temperatures below 5 °C and above 30 °C.

Application in the presence of strong winds can cause cracks in the mortar. In this case, protect the surfaces to minimise the effects of wind.

ISOVIT FIBRA must be coated within 30 days of applying the last layer. In the event of a longer period of time, the condition of the coating and the need for re-rendering should be assessed.

e) Complementary advice

Do not use **ISOVIT FIBRA** to fill joints between insulation panels.

Any mortar that has exceeded its open time must not be applied. Do not soften the mortar by adding water after preparation.

Do not add any other products to the mortar, and **ISOVIT FIBRA** should be applied as shown in the original packaging.

The water in the mix must be free of impurities (clay, organic material), preferably being of drinking quality.

Do not apply to horizontal surfaces or inclines less than 60°.

Protect the upper edges of the rainwater coating.

5. PACKAGING AND VALIDITY

Packaging

Plastic pallets of 60 x 25kg paper bags.

Expiry

12 months, provided the original packaging conditions remain unchanged and in storage conditions protected from extreme temperatures and humidity.

6. HYGIENE AND SAFETY


(DOES NOT PRECLUDE THE PRODUCT SAFETY DATA SHEET)

- Irritant to the eyes, respiratory system and skin
- May cause sensitivity in contact with the skin
- Do not inhale the dust;
- Avoid contact with the skin and eyes;

ISOVIT FIBRA

BONDING AND RENDERING MORTAR FOR EXTERNAL THERMAL INSULATION SYSTEMS

- In case of contact with the eyes, rinse immediately with plenty of water and seek medical advice;
- Wear suitable protective clothing and gloves
- Keep out of the reach of children.

	<p>ISOVIT FIBRA</p> <p>EN 998-1 Industrial mortar for general use (G) for bonding insulation panels</p> <p>Declaration of performance DOP.13001</p>
---	--

Since the conditions of application of our products are out of our control, we cannot be held responsible for their incorrect use. It is the customer's responsibility to verify the suitability of the product for its intended purpose. In any case our liability is limited to the value of the goods provided by us. The information contained in this factsheet may be changed without notice. In case of doubt, and should you require further clarification, we recommend you contact our technical services.

Revised April 2024
FT.13001.04